

Travertino Rojo




Image source: www.redtravertino.com

3 cm

Short description:

brownish-red travertine with massive and sometimes layeres structure. High porosity constituting macropores with perpendicular orientation to layering.

Commodity (vocabulary)	Lithology (vocabulary)	Typical colour (code list)	Place of origin			
			Country	County / District / Province	Municipality / Community	Place/town / Village
Travertine	Travertine	Yellow	Spain	Almería	Alhama de Almería	Alhama de Almería



Geological unit: Travertine of Albox

Application, use and heritage



Images taken from:

García-del-Cura, M.A., Benavente, D., Martínez-Martínez, J., Cueto, N., Rodríguez García, M.A. (2010): travertinos: del imperio romano al siglo XXI. *RockMáquina*, 124:46-49

Description:

The travertines of the southeast of the Iberian Peninsula (Murcia and Almería) have been used in construction since Roman times: the Roman theater of Carthago Nova (1st century BC) to the present (Barcelona's El Prat airport).

Petrography

**Description:**

brownish-red travertine with massive and sometimes layers structure. High porosity constituting macropores with perpendicular orientation to layering.

Travertine with crystalline textures. Crystal size ranges between 2 microns and 2 mm. Crystals can present crystalline fibroradiate and/or arborescent textures. Punctually, micrite layers can be also found. Porosity in this rock is very high with vugs and fenestral pores.

Source of information:

- 1) Geological Survey of Spain (IGME)
- 2) García del Cura, M.A., Benavente, D., Martínez-Martínez, J., Cueto, N. (2012): Sedimentary structures and physical properties in travertines and carbonate tufa building Stone. Construction and Building Materials, 28: 456-467.

Mineral composition

If no accurate number, use MM=main minerals, SM = Subordinate minerals, AM=accessory minerals

Mineral 1 (%)	Mineral 2 (%)	Mineral 3 (%)	Mineral 4 (%)	Mineral 5 (%)	Mineral 6 (%)	Mineral 7 (%)
Calcite (97%)	Muscovite (<1%)	Quartz (1%)	Opaque minerals (2%)			
Mineral 8 (%)	Mineral n (%)					

Source of information:

- 1) Spanish Geological Survey

Physical properties

Apparent density (EN 1936) kg/m ³	Open porosity (EN 1936) % vol	Water absorption at atmospheric pressure (EN 13755) % wt	Uniaxial Compressive strength (EN 1926) MPa	Flexural strength under concentrated load (EN 12372) MPa
2510	5.5		49.48	

Real density (EN 1936) kg/m ³	Total porosity (EN 1936) % vol	Water absorption coefficient by capillary (EN 1925) (g/m ² x s ^{0,5})	Flexural strength under constant moment (EN 13161) MPa
		2.18	

Source of information:

- 1) Spanish Geological Survey (IGME)
- 2) Mármoles y Calizas españoles, 1990, ITGE.
- 3) RocMaquina, Piedras Naturales, maquinaria y equipos. ISSN: 0214-0217.
- 4) Benavente, D., Martínez-Martínez, J., Cueto, N., Ordóñez, S., García-del-Cura, M.A. (2018): Impact of salt and frost weathering on the physical and durability properties of travertines and carbonate tufas used as building material. Environmental Earth Sciences, 77: 147

Sources of more information

Type of information	Name of provider	URL
This data sheet		
Non-commercial directory	Spanish Geological Survey	www.igme.es
Commercial directory	RockMaquina – Piedras naturales, maquinaria y equipos.	
Scientific publication	García del Cura, M.A., Benavente, D., Martínez-Martínez, J., Cueto, N. (2012): Sedimentary structures and physical properties in travertines and carbonate tufa building Stone. Construction and Building Materials, 28: 456-467. Benavente, D., Martínez-Martínez, J., Cueto, N., Ordóñez, S., García-del-Cura, M.A. (2018): Impact of salt and frost weathering on the physical and durability properties of travertines and carbonate tufas used as building material. Environmental Earth Sciences, 77: 147	
Other publication		

Compiled by:	Instituto Geológico y Minero de España (IGME) http://www.igme.es/	 Instituto Geológico y Minero de España
---------------------	--	---