

Crema Levante

Caliza Capri


Crema Pinta



Short description: Fine grained oolitic limestone, with sparitic cement.

Commodity (vocabulary)	Lithology (vocabulary)	Typical colour (code list)	Place of origin			
			Country	County / District / Province	Municipality / Community	Place/town / Village
limestone	oolitic limestone	beige	Spain	Murcia	Lorca	Zarcilla de Ramos

Geological setting



Geology: White or cream colored oolitic or pisolitic limestones from the Almirez Unit (Penibetico). Sometimes the material observed between the oolites is silicified. In thin section Lamellibranchs, Echinoderms, Algae, Gastropods, Bryozoans and *Protoperenoplis striatus* are observed.

Production: Production from various quarry holes in the area.

Geological age: Hettangian/ Callovian (201.3 to 163.5 Ma).

Geological unit: Almirez Unit (Penibetico).

Application, use and heritage



Description: Floor of an edification.

Physical properties

Apparent density (EN 1936) kg/m ³	Open porosity (EN 1936) % vol	Water absorption at atmospheric pressure (EN 13755) % wt	Uniaxial Compressive strength (EN 1926) MPa	Flexural strength under concentrated load (EN 12372) MPa
2660		0,2	131,6	13,2

Real density (EN 1936) kg/m ³	Total porosity (EN 1936) % vol	Water absorption coefficient by capillary (EN 1925) (g/m ² x s ^{0,5})	Flexural strength under constant moment (EN 13161) MPa

Frost resistance (EN 12371)				
Technological Test (Test A)				Identification Test (Test B): Number of cycles completed prior to stone failure
Flexural strength (EN 12372) after freeze-thaw cycling, MPa	Number of cycles	Uniaxial compressive strength (EN 1926) after freeze-thaw cycling, MPa	Number of cycles	

Resistance to ageing by thermal shock (EN 14066)			
Change in dynamic modulus of elasticity (increase: +; decrease: -) %	Change in open porosity (increase: +; decrease: -) %	Change in ultrasound pulse velocity (increase: +; decrease: -) %	Change in flexural strength under conc. load (increase: +; decrease: -) %

Abrasion resistance (EN 14157)			Resistance to salt crystallisation (EN 12370)	Breaking load at dowel hole (EN 13364)	
Method A - Wide Wheel Abrasion Test, mm	Method B - Böhme Abrasion Test, cm ³ / 50cm ²	Method C - Amsler Abrasion Test, mm	Change in mass (increase: +; decrease: -), %	Breaking load, N	Thickness of the test specimens, mm

Slip resistance by means of the pendulum tester (EN 14231 / CEN/TS 16165)			Rupture energy (EN 14158), Joule	Thermal Conductivity (EN 1745), W/m·K
Tested surface finish	Slip Resistance Value — SRV			
	Dry test condition	Wet test condition		

Source of information: <https://rocanatural.es/marmol/crema-levante>

Sources of more information

Type of information	Name of provider	URL
This data sheet	Instituto Geológico y Minero de España (IGME)	http://www.igme.es/
Non-commercial directory		
Commercial directory		
Scientific publication		
Other publication		

Compiled by:	Instituto Geológico y Minero de España (IGME) http://www.igme.es/	 Instituto Geológico y Minero de España
---------------------	--	--